

ABSORBANT CHIMIQUE INDUSTRIEL

BLINKER
PROFESSIONAL COMPONENTS

PAG. 1 DE 1

BLINKER
PROFESSIONAL COMPONENTS**BLINKER**
PROFESSIONAL COMPONENTS**ANALYSES MINERALES (DRX) :**

Sépiolite	75% (minimum 65%)
Densité (BS 1460)	0.64g/cc (maximum 0.71g/cc)
PH	8.5 + 1.0

CAPACITE D'ABSORPTION:

Eau	130% (minimum 100%)
Huile	60% (minimum 50%)
Humidité	maximum 11%

COMPOSITION GRANULOMETRIQUE:

> 1.18mm	maximum 1%
1.18 – 0.60 mm	minimum 92%
0.60 – 0.25 mm	maximum 7%
< 0.25 mm	maximum 1.5%

PRODUIT CHIMIQUE